TECHNICAL DATA SHEET



Air Cushion Film - AEOLOS Blue Ocean

Description

· Polyethylene Air Cushion Film blue transparent

Base Material

Polyethylen, Copolymere

Additives

Slip additive, Antiblocking agents, Processing aids, Masterbatch blue

Note

This film is not protected against UV radiation.

During storage, processing and utilisation the influence of UV radiation must be excluded. Film contains 100% recycled material.

For further information on this film and its application please contact our technical service.

Basic properties* (typical guide values)

zasie proportios (typical garace raises)			
	Value	Unit	Test Method
Tensile strength MD	≥ 25	N/mm²	DIN EN ISO 527-3
Tensile strength TD	≥ 25	N/mm²	DIN EN ISO 527-3
Strain at break MD	≥ 400	%	DIN EN ISO 527-3
Strain at break TD	≥ 400	%	DIN EN ISO 527-3
Dart Drop	≥ 3	g/µm	ASTM D 1709
Coefficient of friction	≤ 0.25		DIN EN ISO 8295

Conditions of storage

Polyolefins are sensitive to light and UV radiation. Therefore the films should be stored in original packaging and kept safe from light. The following storage condition should be kept: Temperature 15 - 30°C, relative humidity 40 - 65%. If this is not possible, then the rolls should be stored in the production area 48 hours before converting (acclimatisation). The converting should be done within 6 months (or 3 months for films containing slip agent), after producing the film.

Environmental compatibility: Polyethylene is ground water neutral and recyclable 100%.

General information

All details of this specification are given to the best of our knowledge. However the data on the sheet are to be seen as general recommendation and not as guarantee for special properties. To check suitability of the material is part of the responsibility of the user of these films.

Date of issue: Mai 2019 — Page 1 of 1